

Bakır ve bakır alaşımları

Tip / Kısa Adı	Elektrotlar											
	2.0926	2.1025	2.1368	2.4366								
Kaynak Malzeme	EL-CuAl9	EL-CuSn 7	EL-CuMn14Al	EL-NiCu 30 Mn								
	CARBO ALBRO AC	CARBO ZIBRO 6 AC	CARBOTRODE Mn-S	CARBOWELD 190								
Ana Malzeme												

2.0220	CuZn5		O									
2.0230	CuZn10		O									
2.0240	CuZn15		O									
2.0241	G-CuZn15		O									
2.0250	CuZn20		O									
2.0261	CuZn28		O									
2.0265	CuZn30		O									
2.0280	CuZn33		O									
2.0321	CuZn37		O									
2.0335	CuZn36		O									
2.0360	CuZn40		O									
2.0460	CuZn20Al2		O									
2.0470	CuZn28Sn1		O									
2.0490	CuZn31Si1		O									
2.0492	G-CuZn15Si4		O									
2.0510	CuZn37Al1		O									
2.0530	CuZn38Sn1		O									
2.0540	CuZn35Ni2		O									
2.0550	CuZn40Al2		O									
2.0572	CuZn40Mn2		O									
2.0590	G-CuZn40Fe		O									
2.0592	G-CuZn35Al1		O									
2.0596	G-CuZn34Al2		O									
2.0598	G-CuZn25Al5		O									
2.0730	CuNi12Zn24			●								
2.0740	CuNi18Zn20			●								
2.0815	G-CuNi10			●								
2.0830	CuNi25			●								
2.0835	G-CuNi30			●								
2.0842	CuNi44Mn1			●								
2.0872	CuNi10Fe1Mn			●								
2.0882	CuNi30Mn1Fe			●								
2.0890	CuNi30Mn			●								
2.0916	CuAl5	●										
2.0920	CuAl8	●										
2.0928	G-CuAl9	●										
2.0960	CuAl9Mn2			●								
2.0962	G-CuAl8Mn			●								
2.0966	CuAl10Ni5Fe4			●								
2.0970	G-CuAl9Ni			●								
2.0971	CuAl9Ni3Fe2			●								
2.0975	G-CuAl10Ni			●								
2.0978	CuAl11Ni6Fe5			●								
2.0980	G-CuAl11Ni			●								
2.1010	CuSn2		●									
2.1016	CuSn4		●									
2.1020	CuSn6		●									
2.1030	CuSn8		●									
2.1050	G-CuSn10		◆									
2.1052	G-CuSn12		◆									
2.1056	G-CuSn14		◆									
2.1060	G-CuSn12Ni		◆									
2.1080	CuSn6Zn6		◆									
2.1086	G-CuSn10Zn		◆									
2.1090	G-CuSn7ZnPb		◆									
2.1093	G-CuSn6ZnNi		◆									
2.1096	G-CuSn5ZnPb		◆									

- Uygun, tür benzeri O Uygun, benzemeyen türler
 ◆ Uygun, Korozyon dayanımına dikkat ediniz.